

TECHNICAL DATA

EP90-1

Low Emitting Sealant/Filler Complies with:

• USGBC LEED Program - Zero VOC's

. . .

1. Product Name Edge-Pro 90

2. Manufacturer

METZGER/MCGUIRE

PO Box 2217 Concord, NH 03302 (USA) Phone: 603-224-6122 Fax: 603-224-6020 Web: www.metzgermcguire.com

3. Product Description

Composition:

Edge-Pro 90 is a two-part, 100% solids, rapid-setting polyurea polymer liquid system. When cured, **Edge-Pro 90** is a rubberlike solid with a hardness of Shore A 90-92.

Basic Use

Edge-Pro 90 was developed to fill and protect joints in heavy duty industrial concrete floors subjected to frequent and demanding traffic. Its primary function is to protect joint edges from spalling under material handling vehicle traffic. **Edge-Pro 90** is intended for use where final operating temperatures are 20°F (-7°C) to 120°F (49°C).

Other Uses:

Edge-Pro 90 is also ideal for filling/repairing random cracks and repairing joints in heavy duty industrial concrete floors.


4. Limitations

Edge-Pro 90 is not recommended for use under VCT or other non-breathable flooring systems.

Edge-Pro 90 is designed for interior use and may not be suitable for outdoor applications due to thermal movement.

5. Correct Joint Design/Installation

Edge-Pro 90 should be installed full joint depth in sawcut contraction/control joints (or 2" minimum in saw-cut joints exceeding 2" in depth) per PCA and ACI guidelines.



In construction (formed) joints that are not saw-cut, **Edge-Pro 90** should be installed at a minimum 2" depth. **DO NOT USE COMPRESSIBLE BACKER ROD IN STANDARD SAW-CUT CONTRACTION/CONTROL JOINTS!** Rod may be used 2" down in construction or saw-cut joints exceeding 2" in depth ONLY.

6. Advantages

Edge-Pro 90's revolutionary new chemistry provides for heavy duty durability, a flush finished profile and better moisture tolerance than many comparable polyurea joint fillers.

- Edge-Pro 90 Finishes Flusher with the Floor Surface Edge Pro 90's chemistry permits for a wider shave window in which the installer can razor off overfill and achieve a consistently flush profile with floor surface.
- Edge-Pro 90 is Less Reactive to Moisture
 Edge-Pro 90 is less reactive to moisture than comparable
 polyurea fillers and its special adhesion enhancers permit better
 adhesion to moist substrates with minimal compromise as compared
 to dry substrates.
- Edge-Pro 90 is Colorfast
 Edge-Pro 90 maintains a consistent color profile and resists fading, yellowing or other discoloration under normal conditions.
- Edge-Pro 90 Provides Unequalled Durability
 Edge-Pro 90 is the first heavy duty polyurea to provide
 comparable properties and durability to our Industry Standard
 MM-80 and MM-80P Heavy Duty Epoxy Joint Fillers. Additional
 benefits include rapid access time to floor areas, reduced material
 loss through joint shrinkage crack, and no heating of the material is
 required during the overfill removal operation.

7. Color, Packaging and Accessories

Standard color is Dovetail Gray. Additional colors options are available through special arrangement. Contact Metzger/McGuire for additional details. Available in 10 gallon (US) kits (2-5 gallon US pails) and 600 ML (300:300) dual cartridge kits.

8. Applicable Specifications

There are no government or ASTM standards for semi-rigid floor joint fillers. **Edge-Pro 90** meets or exceeds the floor joint filler guidelines set forth by the American Concrete Institute's technical committee guides 301-10, 302.1R-15, 310R-13, 360R-10 and the Portland Cement Association's (PCA) Concrete Floors on Ground (2008).

9. USDA/FDA/CFIA/LEED® Approval

Edge-Pro 90 is acceptable for use in USDA, FDA, and CFIA regulated facilities. **Edge-Pro 90** contains no VOC's and is fully compliant with USGBC LEED® green building standards.

10. TECHNICAL PROPERTIES

TEST	METHOD	RESULTS
HARDNESS, SHORE A @ 70°F	D-2240	90-92
TENSILE STRENGTH	D-638	920 psi
TENSILE ELONGATION	D-638	238%
VISCOSITY PART A POLYOL	-	1535 cP
VISCOSITY PART B ISO	-	2500 cP
TACK FREE @ 70°F	-	10-15 minutes
GEL TIME @70°F	-	45-50 seconds
TRAFFIC READY @70°F	-	45 minutes
MIX RATIO (BY VOL.)	-	1:1
		REVISED 04/19

Customer Service - (800) 223-MM80 - Technical Assistance



10. Technical Assistance

Complete technical support and literature are available from authorized distributors, through our web site (www.metzgermcguire.com) or by contacting our New Hampshire headquarters at (800) 223-MM80.

11. Where to Specify and File

Edge-Pro 90 is exclusively for use in industrial concrete floors and thus should always be referenced in 03251 (expansion/contraction joints) & 03300 (cast-in-place concrete). While not a joint sealant, referencing joint filler in 07900 can be helpful as a cross reference.

12. Quality Installation Programs

Metzger/McGuire offers quality installation assurance programs for qualified projects, including our Gold Seal Program. Contact Metzger/McGuire for more information.

13. Availability

Edge-Pro 90 is available through quality construction supply distributors (listing available at www.metzgermcguire.com) or through our NH headquarters.

14. Installation

The following instructions are ABBREVIATED. Complete instructions are provided with each shipment. **Edge-Pro 90** must be dispensed with dual-feed power dispensing equipment or with pre-filled, dual-dispense cartridge kits. Manual dispensing is impractical due to short working life (45-50 second gel time).

When to Install

The installation of *Edge-Pro 90* should be deferred as long as possible after slab placement, and should not be installed prior to 28 days to ensure adequate adhesion. ACI recommends a slab cure of 60-90 days or longer, to permit for greater concrete shrinkage/joint opening, lessening the expected incidence of joint filler separation. Ambient areas should be stabilized at final operating temperature prior to installation. Refrigerated/frozen goods areas stabilized and held for an additional 7-14 days, or longer if possible. Refer to Technical Bulletins T5 and T6 for additional information.

Joint Preparation

Joints should be completely free of saw laitance, dirt, debris, coatings/sealers and frost or visible moisture. Joint cleaning procedures must accomplish the removal of all of the above. Failure to do so will compromise adhesion. Simply "raking" debris out of joint or vacuuming joint is not an acceptable cleaning method. Preferred methods of joint cleaning include using a dustless concrete saw with diamond abrasive blade (ensure blade is slightly wider than joint or clean both sides). No primer is needed. If unusual conditions are present, contact Metzger/McGuire.

Choking off the base of the joint is not required due to **Edge-Pro 90's** rapid set. Do not use compressible backer rod (Ethafoam, etc) in sawcut joints less than 2" deep.

Prior to Dispensing

Thoroughly read SDS and complete installation instructions prior to opening containers or attempting to dispense. Power dispensing systems should be set to a 1:1 ratio by volume. If installing in cooler temperatures, material should be maintained at a minimum temperature of 70°F (23°C) for best results. In warmer temperatures, cooling of product may be necessary.

We recommend the use of a 1/2" diameter (ID) static mixer with 30 or 32 elements for material dispensing and proper mix. Performing periodic ratio checks on power dispense units to ensure proper cure is critical.

Part A polyol should be pre-mixed, using Jiffy Mixer or similar for 1.5 to 2 minutes. Pump tanks, lines and dispensing manifold should be clean and free of any residual materials remaining from previous filler installations.

Dispensina

Joints can be filled in one or two passes, depending upon joint depth and dispensing tip used. Preferred method is to fill from bottom to top, taking care not to entrap air bubbles.

Slightly overfill the joint, leaving a crowned profile, and allow to cure. If using two pass method, second pass should be done while 1st pass is still tacky.

Finishing

The crown may be easily razored off as early as 15 minutes after placement, depending upon temperature. We recommend testing various shave times to find the optimal shave, which results in a filler profile that is flush with the floor's surface and free of any film from material overfill. If shave time is substantially delayed or if temperatures are low, **Edge-Pro 90** shaving process may be more labored.

Should filler cure below the floor surface (due to settlement into the void at base of joint, etc.), remove top $\frac{1}{2}$ of filler and re-apply **Edge-Pro 90**.

Cleanup

Spills of unmixed components can be cleaned up with solvent (MEK, denatured alcohol, etc) or scraped/shaved off floor and tools if cured.

15. Maintenance

Once cured, **Edge-Pro 90** is basically maintenance free if joint dimensions remain static. If joints should widen after installation (due to concrete drying shrinkage), separation voids may occur within the material or between the material and the joint sidewall. Voids exceeding 1/32" should be considered for restoration to ensure joint edge protection. Voids may be filled with additional **Edge-Pro 90**, either through gravity feeding or removal and replacement of top ½" min. of installed filler. Refer to Technical Bulletin T11 (Joint Filler Separation; Causes & Corrections) for additional information.

Edge-Pro 90 can also experience protrusion above the floor surface if put into substantial compression. Joint dimension narrowing (resulting from concrete slab re-hydration/expansion) is a typical cause of this behavior. Please contact *Metzger/McGuire* if unusual circumstances are present, either prior to or after installation. Refer to Technical Bulletin T14 (Joint Filler Protrusion in Exposed Concrete Floors) for additional information.

16. Approximate Coverage Chart			
Joint Size (US)	LF/Gal.	Joint Size (Metric) M/Gal.	
1/8" x 1-1/2"	100	3 x 38	30
1/8" x 1-3/4"	85	3 x 44	26
1/8" x 2"	<i>7</i> 5	3×50	23
3/16" x 3/4"	135	5 x 19	41
3/16" x 1"	100	5 x 25	30
3/16" x 1-1/4"	85	5 x 31	26
3/16" x 1-1/2"	70	5 x 38	21
3/16" x 1-3/4"	60	5 x 44	18
3/16" x 2"	50	5 x 50	15
1/4" x 1"	80	6 x 25	24
1/4" x 1-1/4"	60	6 x 31	18
1/4" x 1-1/2"	50	6 x 44	14
1/4" x 1-3/4"	45	6 x 50	12
1/4" x 2"	40	9 x 25	15
l '			

17. Safety

This product is for industrial use only. Use only in well-ventilated areas. Practice all normal jobsite safety precautions (clear work area, etc). Refer to SDS and installation instructions for more information.

18. Food Related Facilities

Edge-Pro 90 is acceptable for use in facilities regulated by USDA/FDA/CFIA. Contact us to discuss project details if contamination is a concern.

REVISED 04/19

WARRANTY: Metzger/McGuire Co. solely and expressly warrants that its product shall be free from defects in material and workmanship for 12 months from the date of purchase. Unless authorized in writing by an officer of Metzger/McGuire, no other representations or statements made by Metzger/McGuire or its representatives, in writing or orally, shall alter this warranty. Metzger/McGuire makes no warranties, implied or otherwise, as to the merchantability or fitness for ordinary or particular purposes of its products and excludes the same. If any Metzger/McGuire product fails to conform with this warrant, Metzger/McGuire will replace the product at no cost to the purchaser's sole remedy in any case shall be limited to the purchase price or replacement cost of product and specifically excludes labor and the cost of labor, lost wages and opportunity costs, and all other possible incidental, consequential or special damages resulting from any claim of breach of warranty, breach of contract, negligence or any legal theory. Any warranty claim must be made within one [1] year from the date of material purchase. Metzger/McGuire does not authorize anyone on its behalf to make any written or oral statements which in any way alter the installation procedures or written installation instructions published in its product literature or on its packaging labels. Any installation of Metzger/McGuire's products for the purchaser's intended purpose.